



KRONOSWISS

BY SWISS KRONO GROUP

TECHNICAL DATA

TEST STANDARD	TEST INSTITUTE	TEST	RESULTS
EN 13329	WKI	Resistance to impact test	Impact Test Category NK 23-31: IC1, NK 32: IC2, NK 33: IC3
EN 120	WKI	Formaldehyde content	E1 HDF
EN 13329	WKI	Resistance to staining	Group 1-2: Level 5, Group 3: Level 4
EN 13329	WKI	Light fastness	Blue wool scale: Not worse than 6, Grey scale: Not worse than 4
EN 13329	WKI	Resistance to burning cigarette	Level 4
EN 13501-1	MPA	Reaction to fire	Cfl-s1 (flame retardant)
EN 13329	WKI	Effect of a moving furniture leg	No visible reaction to coaster type 0
EN 13329	WKI	Effect of a castor chair	No visible changes or damage, as defined in EN 425
DIN EN 12667	eph	Thermal resistance	$R^{10}_{23/50}$ [(m ² K)/W] 7 mm: 0,054 8 mm: 0,059 10 mm: 0,075 12 mm: 0,089
		Disposal	Disposal as per household waste